

ANALYSIS REPORT

BA - 858/2021

NESKRID 4ALLFEET B.V.

VAN DER DUINSTRAAT 42

5161 BP

NETHERLANDS

NL

BA - 858/2021

(São João Madeira - Física)

EPI-124/2020

DOLCE S3 SRC

Removable insock
Metallic toe cap
Metallic insert protection

General Data

Date of reception:	10/02/2021	Date conditioning:	10/02/2021
Date of testing start:	15/02/2021	Date of testing conclusion:	10/03/2021
		Issue Report:	11/03/2021

Material(s):

Item	Material description:	Reference	Material Type	Material ID
01	One pair of black shoes, size 35	DOLCE		
02	One pair of black shoes, size 42	DOLCE		
03	One pair of black shoes, size 46	DOLCE		
04	One pair of black insocks, size 35	Neskrid NS insocks		
05	One pair of black insocks, size 42	Neskrid NS insocks		
06	One pair of black insocks, size 46	Neskrid NS insocks		
07	Insock removed from item 01	original insocks		
08	Insock removed from item 02	original insocks		
09	Insock removed from item 03	original insocks		
10	Item 01 with item 04 (Neskrid NS insocks)			
11	Item 02 with item 05 (Neskrid NS insocks)			
12	Item 03 with item 06 (Neskrid NS insocks)			

Test Results

Test	Standard	Unit	Item	Result	Specification	Conformity	Note
------	----------	------	------	--------	---------------	------------	------

Whole footwear

Energy absorption of seat region

-- --	EN ISO20344-5.14-2011	J	10	56 / 66	min 20 J (E)	Pass	a
-- --	EN ISO20344-5.14-2011	J	11	98 / 85	min 20 J (E)	Pass	a
-- --	EN ISO20344-5.14-2011	J	12	70 / 80	min 20 J (E)	Pass	a

Determination of antistatic properties

sede
Rua de Fundões Devesa Velha
3700 121 S. João da Madeira
Portugal
telefone +351 256 830 950
fax +351 256 832 554

email geral@ctcp.pt
site www.ctcp.pt



ANALYSIS REPORT

BA - 858/2021

Electrical resistance: dry conditioning	EN ISO20344-5.10-2011	MΩ	10	187 / 288	>0.1 and <1000	Pass	a
Electrical resistance: dry conditioning	EN ISO20344-5.10-2011	MΩ	11	31 / 34	>0.1 and <1000	Pass	a
Electrical resistance: dry conditioning	EN ISO20344-5.10-2011	MΩ	12	36 / 30	>0.1 and <1000	Pass	a
Electrical resistance: wet conditioning	EN ISO20344-5.10-2011	MΩ	10	2 / 3	>0.1 and <1000	Pass	a
Electrical resistance: wet conditioning	EN ISO20344-5.10-2011	MΩ	11	3 / 3	>0.1 and <1000	Pass	a
Electrical resistance: wet conditioning	EN ISO20344-5.10-2011	MΩ	12	6 / 5	>0.1 and <1000	Pass	a

Insock

Thickness of insock

Neskrid NS insocks	EN ISO20344-7.1-2011	mm		2,0 (+/-0,2)	--	--
Original insocks	EN ISO20344-7.1-2011	mm		3,2 (+/-0,1)	--	--

DOLCE



Outsole of Dolce



Notes:

- 05 The uncertainty calculation presented in brackets, if applicable, was carried out in accordance to the documents: EURACHEM / CITAC GUIDE CG4, DOC ISO GUM and ISO 5725-2, and was taken into account in the assessment of conformity. The uncertainty value was calculated and is expressed by the standard uncertainty multiplied by the expansion factor $K = 2$, which for a normal distribution corresponds to coverage probability of approximately 95%.
- a Right foot / Left foot

Relevant additional information:

It is forbidden the reproduction (except complete) of this Assessment Report without previous authorization. The results mentioned are only reported to the tested materials. The fulfilment of the results is only reported to the tested material and is related to the mentioned standards or guidelines and does not mean that a guarantee is given about the performance of the materials.

Every comment made is out of there accredited CTCP laboratory and is based in the actual knowledge of CTCP. CTCP won't be responsible for any damage or injury that happens to the client in consequence of the information given in the report.

The samples deliver to test would be kept in CTCP for a maximum period of 1 year. After this they will be destroyed.

Sampling is responsibility of the customer and is out the scope of accreditation. The sample was analyzed as received.

All information about the sample description is the customer's responsibility.

Supervisor of Testing Report

Isabel Gonçalves

Isabel Gonçalves

(Technicien of Physical Testing)

sede
Rua de Fundões Devesa Velha
3700 121 S. João da Madeira
Portugal
telefone +351 256 830 950
fax +351 256 832 554

email geral@ctcp.pt
site www.ctcp.pt