

Applicant: CORTINA N.V.
MEERSBLOEM-MELDEN 42,
9700 OUDENAARDE, BELGIUM
Attn: PETER DE MEZURE

Date: Nov 23, 2018

Sample Description:


Three (3) pairs of submitted samples said to be Ladies' Cemented slip on occupational shoes in Black.

Standard : ASTM F2892-18
ASTM F2913-17
Size : US 8 (EUR 39)
Buyer's Name : CORTINA N.V.
Ref. No : OLIVE
Brand : OXPAS
Manufacturer : CORTINA N.V.
Colour : --
Vendor : --
Supplier : --
P.O. No. : --
Ref. : Ladies Causal Nursing Ballerina With M2302 PHYLON/RUBBER sole
Country Of Origin : --
Goods Exported To : --
Date Received/Date Test Started: Nov 14, 2018
Date Final Information Confirmed: Nov 23, 2018


Test Result Please Refer To Attached Page(S).

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch



Huang Ning, Andy
Assistant General Manager





- 1 Static Dissipative Footwear (SD) (ASTM F2412-18a, 10, Conditioned At 22°C (±2°C) And 50% RH (±5%) For 24 h And Testing Performed At The Same Conditions)

			<u>ASTM F2892-18 Requirement</u>	<u>Pass/Fail</u>
Sample 1	Left	5.3 × 10 ⁶ Ω	*	Pass
	Right	5.5 × 10 ⁶ Ω	*	Pass
	One Pair	5.1 × 10 ⁶ Ω	*	Pass
Sample 2	Left	8.6 × 10 ⁶ Ω	*	Pass
	Right	6.8 × 10 ⁶ Ω	*	Pass
	One Pair	6.4 × 10 ⁶ Ω	*	Pass
Sample 3	Left	9.9 × 10 ⁶ Ω	*	Pass
	Right	9.1 × 10 ⁶ Ω	*	Pass
	One Pair	7.1 × 10 ⁶ Ω	*	Pass

Remark: * = SD 10: 1 × 10⁶ Ω ~ 1 × 10⁷ Ω

- 2 Slip Resistance (ASTM F2913-17, Vertical Force: 400 N, 23°C, 50% R.H)

Sample	Size	Test Floor	Lubricant	Modes	Results
-	8 (Left)	Eurotile 2	NaLS	Forward Heel Slip (#)	0.48
				Forward Heel Slip (#)	0.43
		Steel Floor	Glycerine	Forward Heel Slip (#)	0.17
				Forward Heel Slip (#)	0.15

Remark: # = Using Standard Shoemaking Last

Note:

It Must Be Noted That The Slip Resistance Test Carried Out In This Report Denotes An Indication Of Slip Of This Particular Footwear/Component On The Surface Mentioned In The Test Item. It Is Important To Note That Footwear Is Subject To Many Different Conditions Encountered In Everyday Use And That It Is Impossible To Make Footwear Resistant To Slip In All Conditions. Nevertheless, It Is Generally Accepted That Problems Are Minimized If The Guideline Coefficients Of Friction Are Achieved.



End Of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. No copy of the test report(except for full text copy) shall be made without the written approval by Intertek.